

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
09 April 2020 (09.04.2020)



(10) International Publication Number
WO 2020/072625 A1

(51) International Patent Classification:

C23C 16/455 (2006.01) H01L 21/02 (2006.01)
C23C 16/34 (2006.01) C07F 7/12 (2006.01)
C23C 16/56 (2006.01)

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(21) International Application Number:

PCT/US2019/054268

(22) International Filing Date:

02 October 2019 (02.10.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/740,478 03 October 2018 (03.10.2018) US

(71) Applicant: **VERSUM MATERIALS US, LLC** [US/US];
8555 S. River Parkway, Tempe, AZ 85284 (US).

(72) Inventors: **LEI, Xinjian**; 8555 S. River Parkway, Tempe,
AZ 85284 (US). **KIM, Moo-sung**; 8555 S. River Parkway,
Tempe, AZ 85284 (US). **LEE, Se-won**; 8555 S. River Park-
way, Tempe, AZ 85284 (US).

(74) Agent: **ROSSI, Joseph, D.** et al.; Stradley Ronon Stevens
& Young, LLP, 30 Valley Stream Parkway, Great Valley
Corporate Center, Malvern, PA 19355 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,
KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

(54) Title: METHODS FOR MAKING SILICON AND NITROGEN CONTAINING FILMS

(57) Abstract: A method for forming a silicon nitride film that may be carbon doped via a plasma ALD process includes introducing a substrate into a reactor, which is heated to up to about 600°C. At least one silicon precursor as defined herein and having one or two Si-C-Si linkages is introduced to form a chemisorbed film on the substrate. The reactor is then purged of any unconsumed precursors and/or reaction by-products with a suitable inert gas. A plasma comprising nitrogen is introduced into the reactor to react with the chemisorbed film to form the silicon nitride film that may be carbon doped. The reactor is again purged of any reaction by-products with a suitable inert gas. The steps are repeated as necessary to bring the deposited silicon nitride film that may be carbon doped to a predetermined thickness.



WO 2020/072625 A1

TITLE OF THE INVENTION:

METHODS FOR MAKING SILICON AND NITROGEN CONTAINING FILMS

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to U.S. provisional patent application No. 62/740,478, filed on October 3, 2018, the entirety of which is incorporated herein by
5 reference.

FIELD OF THE INVENTION

[0002] The present invention is directed to compositions and methods for the fabrication of an electronic device. More specifically, the invention is directed to compounds, compositions and methods for the deposition of a low dielectric constant (<
10 6.0) and high oxygen ash resistant silicon-containing film such as, without limitation, a stoichiometric silicon nitride, a carbon-doped silicon nitride film, and a carbon-doped silicon oxynitride film.

BACKGROUND OF THE INVENTION

15 **[0003]** Silicon nitride films are used in semiconductor for a variety of applications. For example, the silicon nitride film is used as a final passivation and mechanical protective layer for integrated circuits, a mask layer for selective oxidation of silicon, as one of the dielectric materials in a stacked oxide-nitride-oxide (O-N-O) layer in DRAM capacitor or in 3D NAND flash memory chips, or as a CMP stop layer in a shallow trench isolation
20 application. In one particular application, O-N-O stack in 3D NAND flash requires silicon nitride with low stress and high wet etch rate in phosphoric acid.

[0004] Olsen, "Analysis of LPCVD Process Conditions for the Deposition of Low Stress Silicon Nitride", 5 Materials Science in Semiconductor Process 51 (2002) describes a
25 wide range of process conditions that are used to optimize the deposition of low stress silicon nitride films by low-pressure chemical vapor deposition. The results show that an increase in the index of refraction beyond 2.3 by means of increasing the gas flow did

not reduce the residual stress appreciably but had a significant detrimental effect on the thickness uniformity and deposition rate.

5 [0005] Taylor et al., "Hexachlorodisilane as a Precursor in the LPCVD of Silicon Dioxide and Silicon Oxynitride Films", 136 J. Electrochem. Soc. 2382 (1989) describes growing films of silicon dioxide and silicon oxynitride by LPCVD using gas-phase mixtures of Si_2Cl_6 , N_2 , and NH_3 . Films of silicon dioxide and silicon oxynitride were grown by LPCVD using gas-phase mixtures of HCDS, N_2O , and NH_3 in the temperature range 600-850°C. The deposited silicon dioxide and silicon oxynitride films exhibited low chlorine content, typically <1% atomic percent.

10 [0006] M. Tanaka et al., "Film Properties of Low-k Silicon Nitride Films Formed by Hexachlorodisilane and Ammonia", 147 J. Electrochem. Soc. 2284 (2000) describes a low-temperature process with good step coverage of silicon nitride (SiN) formed by low-pressure chemical vapor deposition (LPCVD) using hexachlorodisilane (HCD).

15 [0007] JP2000100812 describes a method for depositing a film using SiCl_4 and NH_3 as source gases. The substrate surface may be nitrated using NH_3 prior to deposition. An extremely thin film having an improved insulator property is formed. The silicon nitride film is useful as a capacitor insulator film of a semiconductor integrated circuit.

20 [0008] US Pat. No. 6,355,582 describes a method for forming a silicon nitride film wherein the substrate to be subjected to the film formation is heated, and silicon tetrachloride and ammonia gases are supplied to the substrate heated to a predetermined temperature.

25 [0009] US Pat. No. 10,049,882 describes an atomic layer deposition (ALD) method for fabricating a semiconductor device including the step of forming a dielectric layer on a structure having a height difference. The method includes forming a structure with a height difference on a substrate and forming a dielectric layer structure on the structure. Forming the dielectric layer structure includes forming a first dielectric layer including silicon nitride on the structure with the height difference. Forming the first dielectric layer includes feeding a first gas including pentachlorodisilane (PCDS) or diisopropylamine pentachlorodisilane (DPDC) as a silicon precursor, and a second gas including nitrogen
30 components into a chamber including the substrate such that the first dielectric layer is formed in situ on the structure having the height difference.

[0010] PCT Pub. No. WO2018063907 discloses a class of chlorodisilazanes, silicon-heteroatom compounds synthesized therefrom, devices containing the silicon-heteroatom compounds, methods of making the chlorodisilazanes, the silicon-heteroatom compounds, and the devices; and uses of the chlorodisilazanes, silicon-heteroatom compounds, and devices.

[0011] PCT Pub. No. WO2018057677 discloses a composition that includes trichlorodisilane as a silicon precursor for use in film forming. The composition includes the silicon precursor compound and at least one of an inert gas, molecular hydrogen, a carbon precursor, nitrogen precursor, and oxygen precursor. The publication also discloses a method of forming a silicon-containing film on a substrate using the silicon precursor compound and the silicon-containing film formed thereby.

[0012] US Pat. No. 9,984,868 discloses cyclical methods of depositing a silicon nitride film on a substrate. In one embodiment such a method includes supplying a halogen silane as a silicon precursor into a reactor; supplying a purge gas to the reactor; and providing an ionized nitrogen precursor into the reactor to react with the substrate and form the silicon nitride film.

[0013] Finally, US Pub. No. 2009/0155606 discloses cyclical methods of depositing a silicon nitride film on a substrate. In one embodiment a method includes supplying a chlorosilane to a reactor in which a substrate is processed; supplying a purge gas to the reactor; and providing ammonia plasma to the reactor. The method allows a silicon nitride film to be formed at a low process temperature and a high deposition rate. The resulting silicon nitride film has relatively few impurities and a relatively high quality. In addition, a silicon nitride film having good step coverage over features having high aspect ratios and a thin and uniform thickness can be formed.

[0014] There is a need in the art to provide a composition and method using same for depositing high carbon content (e.g., a carbon content of about 10 atomic % or greater as measured by X-ray photoelectron spectroscopy (XPS)) doped silicon-containing films for certain applications within the electronics industry.

[0015] Thus, there is a need to develop a process for forming high quality silicon nitride or carbon-doped silicon nitride using a chemical vapor deposition (CVD) or an atomic layer deposition (ALD) process or an ALD-like process, such as without limitation a cyclic chemical vapor deposition process. One particular application, e.g., O-N-O stack in 3D

NAND flash, requires a silicon nitride, silicon oxynitride, or silicon carboxynitride films which exhibit low stress and/or high wet etch rate in phosphoric acid. Further, it may be desirable to develop a low temperature deposition (e.g., deposition at one or more temperatures of about 500 °C or lower) to improve one or more film properties, such as, without limitation, purity and/or density, in a CVD, an ALD, or an ALD-like process.

[0016] The disclosure of the previously identified patents, patent applications and publications is hereby incorporated by reference.

[0017] There is a need in the art to provide a composition and method using the same for depositing silicon nitride or carbon-doped silicon nitride having the following characteristic: a) a carbon content of about 5 atomic % or less, about 3 atomic % or less, about 2 atomic % or less, about 1 atomic % or even less as measured by X-ray photoelectron spectroscopy (XPS), preferably stoichiometric silicon nitride; b) oxygen content of about 5 atomic % or less, about 3 atomic % or less, about 2 atomic % or less, about 1 atomic % or less as measured by X-ray photoelectron spectroscopy (XPS); step coverage of 90 % or higher, 95% or higher, 99% or higher.

BRIEF SUMMARY OF THE INVENTION

[0018] The above-described needs are met in one respect by providing a method for forming a silicon nitride film that may be carbon doped via a plasma ALD process. According to the method, a substrate that includes a surface feature is introduced into a reactor. The reactor is heated one or more temperatures ranging up to about 600°C. The reactor may be maintained at a pressure of 100 torr or less. At least one silicon precursor is introduced into the reactor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane to form a chemisorbed film on the substrate.

[0019] The reactor is then purged of any unconsumed precursors and/or reaction by-products with a suitable inert gas. A plasma comprising nitrogen is introduced into the reactor to react with the chemisorbed film to form the silicon nitride film that may be carbon doped.

5 [0020] Next, the reactor is again purged of any reaction by-products with a suitable inert gas. The steps of introducing the precursor(s), purging as necessary, introducing the plasma, and again purging as necessary, are repeated as necessary to bring the deposited silicon nitride film that may be carbon doped to a predetermined thickness.

[0021] The above-described needs and others are yet further met by a method for
10 forming a silicon nitride, carbon-doped silicon nitride, or carbon-doped silicon oxynitride film via a plasma ALD process. According to the method, a substrate that includes a surface feature is introduced into a reactor. The reactor is heated one or more temperatures ranging up to about 600°C. The reactor may be maintained at a pressure of 100 torr or less. At least one silicon precursor is introduced into the reactor having one
15 or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-
20 1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, and 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane to form a chemisorbed film on the substrate.

25 [0022] The reactor is purged of any unconsumed precursors and/or reaction by-products with a suitable inert gas. A plasma that includes an ammonia source is introduced into the reactor to react with the chemisorbed film to form a silicon nitride or carbon-doped silicon nitride film.

[0023] Next, the reactor is again purged of any reaction by-products with a suitable
30 inert gas. The steps of introducing the precursor(s), purging as necessary, introducing the plasma, and again purging as necessary, are repeated as necessary to bring the silicon nitride or carbon-doped silicon nitride film to a predetermined thickness.

[0024] Optionally the resulting silicon nitride or silicon carbon-doped silicon nitride film is then exposed to an oxygen source at one or more temperatures ranging from about ambient temperature to 1000°C, preferably from about 100° to 400°C, to convert the silicon nitride film into a silicon oxynitride film, or to convert the carbon-doped silicon nitride film into a carbon-doped silicon oxynitride film.

DETAILED DESCRIPTION OF THE INVENTION

[0025] Throughout the description, the term “ALD or ALD-like” refers to a process including, but not limited to, the following processes: a) each reactant including silicon precursor and reactive gas is introduced sequentially into a reactor such as a single wafer ALD reactor, semi-batch ALD reactor, or batch furnace ALD reactor; b) each reactant including silicon precursor and reactive gas is exposed to a substrate by moving or rotating the substrate to different sections of the reactor and each section is separated by inert gas curtain, i.e. spatial ALD reactor or roll to roll ALD reactor.

[0026] Throughout the description, the term “plasma including/comprising ammonia” refers to a reactive gas or gas mixture generated in situ or remotely via a plasma generator. The gas or gas mixture is selected from the group consisting of ammonia, a mixture of ammonia and helium, a mixture of ammonia and neon, a mixture of ammonia and argon, a mixture of ammonia and nitrogen, a mixture of ammonia and hydrogen, and combinations thereof.

[0027] Throughout the description, the term “inert gas plasma” refers to a reactive inert gas or inert gas mixture generated in situ or remotely via a plasma generator. The inert gas or gas mixture is selected from the group consisting of helium, neon, argon, and combination thereof.

[0028] Throughout the description, the term “ashing” refers to a process to remove the photoresist or carbon hard mask in semiconductor manufacturing process using a plasma comprising oxygen source such as O₂/inert gas plasma, O₂ plasma, CO₂ plasma, CO plasma, H₂/O₂ plasma or combination thereof.

[0029] Throughout the description, the term “damage resistance” refers to film properties after oxygen ashing process. Good or high damage resistance is defined as the following film properties after oxygen ashing: film dielectric constant lower than 6;

carbon content in the bulk (at more than 50 Å deep into film) is within 5 at. % as before ashing; less than 50 Å of the film is damaged, observed by differences in dilute HF etch rate between films near surface (less than 50 Å deep) and bulk (more than 50 Å deep).

5 [0030] Throughout the description, the term “alkyl hydrocarbon” refers to a linear or branched C₁ to C₂₀ hydrocarbon, or cyclic C₆ to C₂₀ hydrocarbon. Exemplary hydrocarbons includes but are not limited to, heptane, octane, nonane, decane, dodecane, cyclooctane, cyclononane, and cyclodecane.

10 [0031] Throughout the description, the term “aromatic hydrocarbon” refers to a C₆ to C₂₀ aromatic hydrocarbon. Exemplary aromatic hydrocarbons include, but are not limited to, toluene and mesitylene.

15 [0032] Throughout the description, the term “step coverage” as used herein is defined as a percentage of two thicknesses of the deposited film in a structured or featured substrate having either vias or trenches or both, with bottom step coverage being the ratio (in %): thickness at the bottom of the feature is divided by thickness at the top of the feature, and middle step coverage being the ratio (in %): thickness on a sidewall of the feature is divided by thickness at the top of the feature. Films deposited using the method described herein exhibit a step coverage of about 80% or greater, or about 90% or greater which indicates that the films are conformal.

20 [0033] Throughout the description, the term “plasma comprising ammonia” refers to a reactive gas or gas mixture generated in situ or remotely via a plasma generator. The gas or gas mixture is selected from the group consisting of ammonia, a mixture of ammonia and helium, a mixture of ammonia and neon, a mixture of ammonia and argon, a mixture of ammonia and nitrogen, a mixture of ammonia and hydrogen, nitrogen, a mixture of nitrogen and helium, a mixture of nitrogen and neon, a mixture of nitrogen and argon and combinations thereof.

25 [0034] Throughout the description, the term “plasma including/comprising nitrogen” refers to a reactive gas or gas mixture generated in situ or remotely via a plasma generator. The gas or gas mixture is selected from the group consisting of nitrogen, a mixture of nitrogen and helium, a mixture of nitrogen and neon, a mixture of nitrogen and argon, a mixture of ammonia and nitrogen, a mixture of nitrogen and hydrogen, and combinations thereof.


30

[0035] Described herein are silicon precursor compositions, and methods comprising such compositions, to deposit silicon nitride or carbon-doped silicon nitride having the following characteristics: a) a carbon content of about 5 atomic % or less, about 3 atomic % or less, about 2 atomic % or less, about 1 atomic % or even less as measured by X-ray photoelectron spectroscopy (XPS), preferably stoichiometric silicon nitride; b) oxygen content of about 5 atomic % or less, about 3 atomic % or less, about 2 atomic % or less, about 1 atomic % or less as measured by X-ray photoelectron spectroscopy (XPS); step coverage of 90 % or higher, 95% or higher, or 99% or higher.

In one aspect, the composition for depositing a silicon-containing film comprises: (a) at least one silicon precursor compound having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane; and (b) at least one solvent.

20

[0036] Table 1. Silicon precursors having one Si-C-Si linkage















Table 2. Silicon precursors having two Si-C-Si linkages



5

[0037] In certain embodiments of the composition described herein, exemplary solvents can include, without limitation, ether, tertiary amine, alkyl hydrocarbon, aromatic

hydrocarbon, tertiary aminoether, siloxanes, and combinations thereof. In certain embodiments, the difference between the boiling point of the compound having one Si-C-Si or two Si-C-Si linkages and the boiling point of the solvent is 40°C or less. The wt % of silicon precursor compound in the solvent can vary from 1 to 99 wt %, or 10 to 90 wt%, or 20 to 80 wt %, or 30 to 70 wt %, or 40 to 60 wt %, to 50 to 50 wt %. In some embodiments, the composition can be delivered via direct liquid injection into a reactor chamber for silicon-containing film using conventional direct liquid injection equipment and methods. In one embodiment of the method described herein, the silicon nitride or carbon-doped silicon nitride film has a carbon content less than 5 at. % or less and deposited using a plasma enhanced ALD process. In this embodiment, the method comprises:

- a. placing one or more substrates comprising a surface feature into a reactor and heating the reactor to one or more temperatures ranging from ambient temperature to about 600°C and optionally maintaining the reactor at a pressure of 100 torr or less;
- b. introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane;
- c. purging with an inert gas thereby removing any unreacted silicon precursor;
- d. providing a plasma comprising an ammonia source into the reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film; and
- e. purging with inert gas to remove any reaction by-products;

wherein the steps b through e are repeated until a desired thickness of film is deposited. In certain embodiments, the method described herein further comprises:

- 5
- f. optionally post-deposition treating the silicon nitride or carbon-doped silicon nitride film carbon-doped film with a thermal anneal or a spike anneal at temperatures from 400 to 1000C or a UV light source. In this or other embodiments, the UV exposure step can be carried out either during film deposition, or once deposition has been completed.
- 10
- g. optionally providing post-deposition exposing the carbon-doped silicon nitride film to a plasma comprising hydrogen or inert gas or nitrogen to improve at least one of the films' physical properties

[0038] In another embodiment of the method described herein, the silicon nitride or carbon-doped silicon nitride film has a carbon content of 5 at. % or less and is deposited using a plasma enhanced ALD process. In this embodiment, the method comprises:

- 15
- a. placing one or more substrates comprising a surface feature into a reactor (e.g., into a conventional ALD reactor) and heating to reactor to one or more temperatures ranging from ambient temperature to about 600°C and optionally maintaining the reactor at a pressure of 100 torr or less;
- 20
- b. introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane;
- 25
- 30
- c. purging with an inert gas;

- d. providing a plasma including/comprising an ammonia source into the reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film;
- e. purging with inert gas to remove reaction by-products;

5 wherein the steps b through e are repeated until a desired thickness of film is deposited. In certain embodiments, the method described herein further comprises:

- f. optionally post-deposition treating the silicon nitride or carbon-doped silicon nitride film with a spike anneal at temperatures from 400 to 1000C or a UV light source. In this or other embodiments, the UV exposure step
10 can be carried out either during film deposition, or once deposition has been completed;
- g. optionally providing post-deposition exposing the silicon nitride or carbon-doped silicon nitride film to a plasma comprising hydrogen or inert gas or nitrogen to improve at least one of the films' physical properties.

15 **[0039]** In another embodiment of the method described herein, the carbon-doped silicon oxynitride has a carbon content 5 at. % or less and is deposited using a plasma enhanced ALD process. In this embodiment, the method comprises:

- a. placing one or more substrates comprising a surface feature into a reactor (e.g., into a conventional ALD reactor) and heating to reactor to one or
20 more temperatures ranging from ambient temperature to about 600°C and optionally maintaining the reactor at a pressure of 100 torr or less;
- b. introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane,
25 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-

30

pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane;

- c. purging with an inert gas;
- d. providing a plasma including/comprising ammonia source into the reactor to react with the surface to form a silicon nitride film;
- e. purging with inert gas to remove reaction by-products;

wherein the steps b through e are repeated until a desired thickness of film is deposited. In certain embodiments, the method described herein further comprises;

- f. providing post-deposition treating the silicon nitride or carbon-doped silicon nitride film with an oxygen source at one or more temperatures ranging from about ambient temperature to 1000°C or from about 100° to 400°C to convert the silicon nitride or carbon-doped silicon nitride film into a carbon-doped silicon oxynitride film either in situ or in another chamber.

[0040] In yet another embodiment of the method described herein, the silicon nitride or carbon-doped silicon nitride film having a carbon content less than 5 at. % is deposited using a plasma enhanced ALD process. In this embodiment, the method comprises:

- a. placing one or more substrates comprising a surface feature into a reactor and heating the reactor to one or more temperatures ranging from ambient temperature to about 600°C and optionally maintaining the reactor at a pressure of 100 torr or less;

- b. introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane;

- 5 c. purging with an inert gas thereby removing any unreacted silicon precursor;
- d. providing a first plasma including/comprising ammonia source into the reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film;
- e. purging with inert gas to remove any reaction by-products;
- f. providing a second plasma including/comprising nitrogen source into the reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film;
- 10 g. purging with inert gas to remove any reaction by-products; and

wherein the steps b through g are repeated until a desired thickness of film is deposited. In certain embodiments, the method described herein further comprises.

[0041] In yet another embodiment of the method described herein, the silicon nitride or carbon-doped silicon nitride film has a carbon content less than 5 at. % or less and deposited using a plasma enhanced ALD process. In this embodiment, the method comprises:

15

- 20 a. placing one or more substrates comprising a surface feature into a reactor and heating the reactor to one or more temperatures ranging from ambient temperature to about 600°C and optionally maintaining the reactor at a pressure of 100 torr or less;
- b. introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages selected from the group consisting of 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-
- 25
- 30

pentachloro-3,3-dimethyl-1,3,5-trisilohexane, 1,1,1,5,5-pentachloro-1,3,5-trisilohexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane;

- c. purging with an inert gas thereby removing any unreacted silicon precursor;
- 5 d. providing a first plasma including/comprising nitrogen source into the reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film;
- e. purging with inert gas to remove any reaction by-products;
- f. providing a second plasma including/comprising ammonia source into the
10 reactor to react with the surface to form a silicon nitride or carbon-doped silicon nitride film;
- g. purging with inert gas to remove any reaction by-products; and

wherein the steps b through g are repeated until a desired thickness of film is deposited.

In one embodiment, the substrate includes at least one feature wherein the feature
15 comprises a pattern trench with an aspect ratio of 1:9 or more, and an opening of 180 nm or less.

[0042] In yet another embodiment, a vessel for depositing a silicon-containing film includes one or more silicon precursor compounds described herein. In one particular embodiment, the vessel is at least one pressurizable vessel (preferably of stainless steel
20 having a design such as disclosed in U.S. Patent Nos. US7334595; US6077356; US5069244; and US5465766 the disclosure of which is hereby incorporated by reference. The container can comprise either glass (borosilicate or quartz glass) or type 316, 316L, 304 or 304L stainless steel alloys (UNS designation S31600, S31603, S30400 S30403) fitted with the proper valves and fittings to allow the delivery of one or
25 more precursors to the reactor for a CVD or an ALD process. In this or other embodiments, the silicon precursor is provided in a pressurizable vessel comprised of stainless steel and the purity of the precursor is 98% by weight or greater or 99.5% or greater which is suitable for the semiconductor applications. The silicon precursor compounds are preferably substantially free of metal ions such as, Al³⁺ ions, Fe²⁺, Fe³⁺,
30 Ni²⁺, Cr³⁺. As used herein, the term "substantially free" as it relates to Al, Fe, Ni Cr means less than about 5 ppm (by weight) as measured by ICP-MS, preferably less than

about 1 ppm, and more preferably less than about 0.1 ppm as measured by ICP-MS, and most preferably about 0.05 ppm as measured by ICP-MS. In certain embodiments, such vessels can also have means for mixing the precursors with one or more additional precursor if desired. In these or other embodiments, the contents of the vessel(s) can be
5 premixed with an additional precursor. Alternatively, the silicon precursor is and/or other precursor can be maintained in separate vessels or in a single vessel having separation means for maintaining the silicon precursor is and other precursor separate during storage.

[0043] The silicon-containing film is deposited upon at least a surface of a substrate
10 such as a semiconductor or display substrate. In the method described herein, the substrate may be comprised of and/or coated with a variety of materials well known in the art including films of silicon such as crystalline silicon or amorphous silicon, silicon oxide, silicon nitride, amorphous carbon, silicon oxycarbide, silicon oxynitride, silicon carbide, germanium, germanium doped silicon, boron doped silicon, metal such as
15 copper, tungsten, aluminum, cobalt, nickel, tantalum), metal nitride such as titanium nitride, tantalum nitride, metal oxide, group III/V metals or metalloids such as GaAs, InP, GaP and GaN, AMOLED (active matrix organic light-emitting diode) flexible substrates (for example plastic substrates) and a combination thereof. These coatings may completely coat the semi-conductor substrate, may be in multiple layers of various
20 materials and may be partially etched to expose underlying layers of material. The surface may also have on it a photoresist material that has been exposed with a pattern and developed to partially coat the substrate. In certain embodiments, the semiconductor substrate comprising at least one surface feature selected from the group consisting of pores, vias, trenches, and combinations thereof. The potential application of the silicon-
25 containing films include but not limited to low k spacer for FinFET or nanosheet, sacrificial hard mask for self-aligned patterning process (such as SADP, SAQP, or SAOP).

[0044] The deposition method used to form the silicon-containing films or coatings are deposition processes. Examples of suitable deposition processes for the method
30 disclosed herein include, but are not limited to, a chemical vapor deposition or an atomic layer deposition process. As used herein, the term “chemical vapor deposition processes” refers to any process wherein a substrate is exposed to one or more volatile precursors, which react and/or decompose on the substrate surface to produce the

desired deposition. As used herein, the term “atomic layer deposition process” refers to a self-limiting (e.g., the amount of film material deposited in each reaction cycle is constant), sequential surface chemistry that deposits films of materials onto substrates of varying compositions. As used herein, the term “thermal atomic layer deposition
5 process” refers to atomic layer deposition process at substrate temperatures ranging from room temperature to 600°C without in situ or remote plasma. Although the precursors, reagents and sources used herein may be sometimes described as “gaseous”, it is understood that the precursors can be either liquid or solid which are transported with or without an inert gas into the reactor via direct vaporization, bubbling
10 or sublimation. In some case, the vaporized precursors can pass through a plasma generator.

[0045] In one embodiment, the silicon-containing film is deposited using an ALD process. In another embodiment, the silicon-containing film is deposited using a CCVD process. In a further embodiment, the silicon-containing film is deposited using a
15 thermal ALD process. The term “reactor” as used herein, includes without limitation, reaction chamber or deposition chamber.

[0046] In certain embodiments, the method disclosed herein avoids pre-reaction of precursor(s) by using ALD or cyclic CVD methods that separate the precursor(s) prior to and/or during the introduction to the reactor. Deposition techniques such as ALD or
20 CCVD processes are preferably used to deposit the silicon-containing film. In one embodiment, the film is deposited via an ALD process in a typical single wafer ALD reactor, semi-batch ALD reactor, or batch furnace ALD reactor by exposing the substrate surface alternatively to the one or more silicon-containing precursors, oxygen source, nitrogen-containing source, or other precursors or reagents. Film growth proceeds by
25 self-limiting control of the surface reaction, the pulse length of each precursor or reagent, and the deposition temperature. However, once the surface of the substrate is saturated, the film growth ceases. In another embodiment, each reactant including the silicon precursor and reactive gas is exposed to a substrate by moving or rotating the substrate to different sections of the reactor and each section is separated by an inert
30 gas curtain, i.e. a spatial ALD reactor or a roll to roll ALD reactor.

[0047] Depending upon the deposition method, in certain embodiments, the silicon precursors described herein and optionally other silicon-containing precursors may be introduced into the reactor at a predetermined molar volume, such as from about 0.1 to

about 1000 micromoles. In this or other embodiments, the precursor may be introduced into the reactor for a predetermined time period. In certain embodiments, the time period ranges from about 0.001 to about 500 seconds.

[0048] In certain embodiments, the silicon nitride or carbon-doped silicon films deposited using the methods described herein are treated with an oxygen source, reagent or precursor comprising oxygen, e.g. water vapor, to convert such films into carbon-doped oxynitride. An oxygen source may be introduced into the reactor in the form of at least one oxygen source and/or may be present incidentally in the other precursors used in the deposition process. Suitable oxygen source gases may include, for example, air, water (H₂O) (e.g., deionized water, purified water, distilled water, water vapor, water vapor plasma, hydrogen peroxide, oxygenated water, air, a composition comprising water and other organic liquid), oxygen (O₂), oxygen plasma, ozone (O₃), nitric oxide (NO), nitrogen dioxide (NO₂), nitrous oxide (N₂O), carbon monoxide (CO), hydrogen peroxide (H₂O₂), a plasma comprising water, a plasma comprising water and argon, hydrogen peroxide, a composition comprising hydrogen, a composition comprising hydrogen and oxygen, carbon dioxide (CO₂), air, and combinations thereof. In certain embodiments, the oxygen source comprises an oxygen source gas that is introduced into the reactor at a flow rate ranging from about 1 to about 10000 square cubic centimeters (sccm) or from about 1 to about 1000 sccm. The oxygen source can be introduced for a time that ranges from about 0.1 to about 100 seconds. The catalyst is selected from a Lewis base such as pyridine, piperazine, trimethylamine, tert-butylamine, diethylamine, trimethylamine, ethylenediamine, ammonia, or other organic amines.

[0049] In embodiments wherein the film is deposited by an ALD or a cyclic CVD process, the precursor pulse can have a pulse duration that is greater than 0.01 seconds, and the oxygen source can have a pulse duration that is less than 0.01 seconds, while the water pulse duration can have a pulse duration that is less than 0.01 seconds.

[0050] In certain embodiments, the oxygen source is continuously flowing into the reactor while precursor pulse and plasma are introduced in sequence. The precursor pulse can have a pulse duration greater than 0.01 seconds while the plasma duration can range between 0.01 seconds to 100 seconds.

[0051] In certain embodiments, the silicon-containing films comprise silicon and nitrogen. In these embodiments, the silicon-containing films deposited using the methods described herein are formed in the presence of a nitrogen-containing source. A nitrogen-containing source may be introduced into the reactor in the form of at least one nitrogen source gas and/or may be present incidentally in the other precursors used in the deposition process.

[0052] Suitable ammonia-containing gases may include, for example, ammonia, a mixture of ammonia and inert gas, a mixture of ammonia and nitrogen, a mixture of ammonia and hydrogen, and combinations thereof.

[0053] In certain embodiments, the nitrogen source is introduced into the reactor at a flow rate ranging from about 1 to about 10000 square cubic centimeters (sccm) or from about 1 to about 1000 sccm. The nitrogen-containing source can be introduced for a time that ranges from about 0.1 to about 100 seconds. In embodiments wherein the film is deposited by an ALD or a cyclic CVD process using both a nitrogen and oxygen source, the precursor pulse can have a pulse duration that is greater than 0.01 seconds, and the nitrogen source can have a pulse duration that is less than 0.01 seconds, while the water pulse duration can have a pulse duration that is less than 0.01 seconds. In yet another embodiment, the purge duration between the pulses that can be as low as 0 seconds or is continuously pulsed without a purge in-between.

[0054] The deposition methods disclosed herein include one or more steps of purging unwanted or unreacted material from a reactor using purge gases. The purge gas, which is used to purge away unconsumed reactants and/or reaction byproducts, is an inert gas that does not react with the precursors. Exemplary purge gases include, but are not limited to, argon (Ar), nitrogen (N₂), helium (He), neon (Ne), hydrogen (H₂), and combinations thereof. In certain embodiments, a purge gas such as Ar is supplied into the reactor at a flow rate ranging from about 10 to about 10000 sccm for about 0.1 to 1000 seconds, thereby purging the unreacted material and any byproduct that may remain in the reactor.

[0055] The respective steps of supplying the precursors, oxygen source, the ammonia-containing source, and/or other precursors, source gases, and/or reagents may be performed by changing the time for supplying them to change the stoichiometric composition of the resulting film.

[0056] Energy is applied to the at least one of the precursor, ammonia-containing source, reducing agent such as hydrogen plasma, other precursors or combination thereof to induce reaction and to form the film or coating on the substrate. Such energy can be provided by, but not limited to, thermal, plasma, pulsed plasma, helicon plasma, 5 high density plasma, inductively coupled plasma, X-ray, e-beam, photon, remote plasma methods, and combinations thereof.

[0057] In certain embodiments, a secondary RF frequency source can be used to modify the plasma characteristics at the substrate surface. In embodiments wherein the deposition involves plasma, the plasma-generated process may comprise a direct 10 plasma-generated process in which plasma is directly generated in the reactor, or alternatively a remote plasma-generated process in which plasma is generated outside of the reactor and supplied into the reactor.

[0058] The silicon precursors and/or other silicon-containing precursors may be delivered to the reaction chamber, such as a CVD or ALD reactor, in a variety of ways. 15 In one embodiment, a liquid delivery system may be utilized. In an alternative embodiment, a combined liquid delivery and flash vaporization process unit may be employed, such as, for example, the turbo vaporizer manufactured by MSP Corporation of Shoreview, MN, to enable low volatility materials to be volumetrically delivered, which leads to reproducible transport and deposition without thermal decomposition of the 20 precursor. In liquid delivery formulations, the precursors described herein may be delivered in neat liquid form, or alternatively, may be employed in solvent formulations or compositions comprising same. Thus, in certain embodiments the precursor formulations may include solvent component(s) of suitable character as may be desirable and advantageous in a given end use application to form a film on a substrate.

[0059] In this or other embodiments, it is understood that the steps of the methods 25 described herein may be performed in a variety of orders, may be performed sequentially or concurrently (e.g., during at least a portion of another step), and any combination thereof. The respective step of supplying the precursors and the nitrogen-containing source gases may be performed by varying the duration of the time for supplying them to 30 change the stoichiometric composition of the resulting silicon-containing film.

[0060] In a still further embodiment of the methods described herein, the film or the as-deposited film is subjected to a treatment step. The treatment step can be conducted

during at least a portion of the deposition step, after the deposition step, and combinations thereof. Exemplary treatment steps include, without limitation, treatment via high temperature thermal annealing; plasma treatment; ultraviolet (UV) light treatment; laser; electron beam treatment and combinations thereof to affect one or more properties of the film. The films deposited with the silicon precursors having one or two Si-C-Si linkages described herein, when compared to films deposited with previously disclosed silicon precursors under the same conditions, have improved properties such as, without limitation, a wet etch rate that is lower than the wet etch rate of the film before the treatment step or a density that is higher than the density prior to the treatment step.

5

10

In one particular embodiment, during the deposition process, as-deposited films are intermittently treated. These intermittent or mid-deposition treatments can be performed, for example, after each ALD cycle, after a certain number of ALD, such as, without limitation, one (1) ALD cycle, two (2) ALD cycles, five (5) ALD cycles, or after every ten (10) or more ALD cycles.

15

[0061] In an embodiment wherein the film is treated with a high temperature annealing step, the annealing temperature is at least 100°C or greater than the deposition temperature. In this or other embodiments, the annealing temperature ranges from about 400°C to about 1000°C. In this or other embodiments, the annealing treatment can be conducted in a vacuum (< 760 Torr), inert environment or in oxygen containing environment (such as ozone, H₂O, H₂O₂, N₂O, NO₂ or O₂)

20

25

[0062] In an embodiment wherein the film is treated to UV treatment, film is exposed to broad band UV or, alternatively, an UV source having a wavelength ranging from about 150 nanometers (nm) to about 400 nm. In one particular embodiment, the as-deposited film is exposed to UV in a different chamber than the deposition chamber after a desired film thickness is reached.

30

[0063] In an embodiment where in the film is treated with a plasma, passivation layer such as carbon-doped silicon oxide is deposited to prevent chlorine and nitrogen contamination from penetrating film in the subsequent plasma treatment. The passivation layer can be deposited using atomic layer deposition or cyclic chemical vapor deposition.

[0064] In an embodiment wherein the film is treated with a plasma, the plasma source is selected from the group consisting of hydrogen plasma, plasma comprising hydrogen

and helium, plasma comprising hydrogen and argon. Hydrogen plasma lowers film dielectric constant and boost the damage resistance to following plasma ashing process while still keeping the carbon content in the bulk almost unchanged.

5 [0065] The following examples illustrate certain aspects of the instant invention and do not limit the scope of the appended claims.

EXAMPLES

10 [0066] In the following examples, unless stated otherwise, properties will be obtained from sample films that are deposited onto silicon wafer with resistivity of 5-20 Ω-cm as substrate. All film depositions are performed using the CN-1 reactor has showerhead design with 13.56 MHz direct plasma.

[0067] In typical process conditions, unless stated otherwise, the chamber pressure is fixed at a pressure ranging from about 1 to about 5 Torr. Additional inert gas is used to maintain chamber pressure.

15 [0068] The film depositions comprise the steps listed in Tables 3, 4, and 5 for plasma enhanced ALD. Unless otherwise specified, a total of 100 or 200 or 300 or 500 deposition cycles are used to get the desired film thickness.

Table 3. Deposition Steps in PEALD Silicon Nitride or Carbon-doped Silicon Nitride Films

Step	
a	Provide a substrate comprising a surface feature in a reactor and heat the substrate to a desired temperature
b	Introduce vapors of a silicon precursor to the reactor; additional inert gas is used to maintain chamber pressure to provide a chemisorbed layer
c	Purge unreacted the silicon precursor from the reactor chamber with inert gas
d	Introduce a plasma comprising an ammonia source to react with the surface of the chemisorbed layer and create reactive sites
e	Purge reaction by-products out

20 Table 4. Deposition Steps in PEALD Silicon Nitride or Carbon-doped Silicon Nitride Films

Step	
a	Provide a substrate comprising a surface feature in a reactor and heat the substrate to a desired temperature
b	Introduce vapors of a silicon precursor to the reactor; additional inert gas is used to maintain chamber pressure to provide a chemisorbed layer
c	Purge unreacted silicon precursor from the reactor chamber with inert gas
d	Introduce a first plasma comprising an ammonia source to react with the surface of the chemisorbed layer and create reactive sites
e	Purge reaction by-products out
f	Introduce a second plasma comprising a nitrogen source to react with the surface of the chemisorbed layer and create reactive sites
g	Purge reaction by-products out

Table 5: Deposition Steps in PEALD Silicon Nitride or Carbon-doped Silicon Nitride Films

Step	
a	Provide a substrate comprising a surface feature in a reactor and heat the substrate to a desired temperature
b	Introduce vapors of a silicon precursor to the reactor; additional inert gas is used to maintain chamber pressure to provide a chemisorbed layer
c	Purge unreacted silicon precursor from the reactor chamber with inert gas
d	Introduce a first plasma comprising a nitrogen source to react with the surface of the chemisorbed layer and create reactive sites
e	Purge reaction by-products out
f	Introduce a second plasma comprising an ammonia source to react with the surface of the chemisorbed layer and create reactive sites
g	Purge reaction by-products out

- 5 **[0069]** The refractive index (RI) and thickness for the deposited films are measured using an ellipsometer. Film non-uniformity is calculated using the standard equation: %

non-uniformity = ((max thickness – min thickness)/(2*average (avg) thickness)). Film structure and composition are analyzed using Fourier Transform Infrared (FTIR) spectroscopy and X-Ray Photoelectron Spectroscopy (XPS). The density for the films is measured with X-ray Reflectometry (XRR).

5

Example 1: ALD silicon nitride using 1,1,1,3,3-pentachloro-1,3-disilabutane and NH₃/argon plasma

[0070] A silicon wafer was loaded into a CN-1 reactor equipped with a showerhead design with 13.56 MHz direct plasma with a chamber pressure of 1 torr. 1,1,1,3,3-pentachloro-1,3-disilabutane as a silicon precursor, was delivered as vapors into the reactor using bubbling or vapor draw.

[0071] The ALD cycle was comprised of the process steps provided in Table 3 and used the following process parameters:

- a. Provide a substrate in a reactor and heat the substrate to about 300°C
- 15 b. Introduce vapors of 1,1,1,3,3-pentachloro-1,3-disilabutane to the reactor
Argon flow: 100 sccm through precursor container
Pulse: 2 seconds
Ar flow: 1000 sccm
- c. Purge
- 20 Argon flow: 1000 sccm
Purge time: 10 seconds
- d. Introduce ammonia plasma
Argon flow: 1000 sccm
Ammonia flow: 300 sccm
- 25 Plasma power; 300 W
Pulse: 15 seconds
- e. Purge
Argon flow: 1000 sccm
Purge time: 5 seconds

30 Steps b to e were repeated for 1000 cycles to provide 32nm of silicon nitride with a composition of 58.66 at. % nitrogen, 38.96 at. % silicon, and 2.37 at. % oxygen. Both chlorine and carbon were undetectable. The refractive index was about 1.9.

[0072] Example 2: ALD silicon nitride using 1,1,1,3,3-pentachloro-1,3-disilabutane and NH₃/argon plasma

[0073] A silicon wafer was loaded into the CN-1 reactor equipped with showerhead design with 13.56 MHz direct plasma with chamber pressure of 1 torr. 1,1,1,3,3-pentachloro-1,3-disilabutane was delivered as vapors into the reactor using bubbling.

[0074] The ALD cycle was comprised of the process steps provided in Table 1 and used the following process parameters:

- a) Provide a substrate in a reactor and heat the substrate to about 400°C;
- b) Introduce vapors of 1,1,1,3,3-pentachloro-1,3-disilabutane to the reactor;

Argon flow: 100 sccm through precursor container

Pulse: 2 seconds

10 Argon: 1000 sccm

- c) Inert gas purge

Argon flow: 1000 sccm

Purge time: 15 seconds

- d) Introduce ammonia plasma

15 Argon flow: 1000 sccm

Ammonia flow: 50 sccm

Plasma power: 300 W

Pulse: 10 seconds

- e) Purge

20 Argon flow: 1000 sccm

Purge time: 10 seconds

Steps b to e were repeated for 1000 cycles to provide 26nm of silicon nitride with a composition of 58.30 at. % nitrogen, 39.15 at. % silicon, 2.55 at. % oxygen. Both chlorine and carbon were undetectable as measured by XPS. The composition of the resulting film in this working example was close to stoichiometric silicon nitride. The refractive index was about 1.9.

[0075] Although illustrated and described above with reference to certain specific embodiments and working examples, the present invention is nevertheless not intended to be limited to the details shown. Rather, various modifications may be made in the details within the scope and range of equivalents of the claims and without departing from the spirit of the invention. It is expressly intended, for example, that all ranges

broadly recited in this document include within their scope all narrower ranges which fall within the broader ranges.

THE FOLLOWING IS CLAIMED

1) A method for forming a silicon nitride or carbon-doped silicon nitride via a plasma enhanced ALD process, the method comprising:

- 5 a) providing a substrate comprising a surface feature in a reactor and heating the reactor to one or more temperatures ranging up to about 600°C, and optionally maintaining the reactor at a pressure of 100 torr or less;
- 10 b) introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages and selected from the group consisting of 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane, whereby the silicon precursor reacts on at least a portion of the surface feature of the substrate to provide a chemisorbed layer;
- 15 20 25 30 c) purging the reactor of any unreacted silicon precursors and/or any reaction by-products using inert gas;
- d) providing a plasma comprising an ammonia source into the reactor to react with the chemisorbed layer to form a silicon nitride film; and
- e) purging the reactor of any further reaction by-products with inert gas;

wherein the steps b through e are repeated until a desired thickness of the silicon nitride film is deposited.

- 2) The method according to claim 1, wherein the silicon nitride film is a carbon-doped silicon nitride film.
- 5 3) The method according to claim 1, further comprising:
treating the silicon nitride film with a spike anneal at a temperature ranging between 400 and 1000°C.
- 4) The method according to claim 1, further comprising:
10 exposing the silicon nitride film to a UV light source either during or after deposition of the silicon nitride film.
- 5) The method according to claim 1, further comprising:
exposing the silicon nitride film to a plasma comprising one or more gases selected from the group consisting of hydrogen, inert gas, nitrogen, and combinations thereof.
- 15 6) The method according to claim 1, further comprising:
treating the silicon nitride film with an oxygen source at one or more temperatures ranging from ambient temperature to 1000 °C to convert the silicon nitride into a silicon oxynitride film, either in situ or in a separate chamber from the reactor.
- 20 7) The method according to claim 6, wherein the silicon nitride film is a carbon-doped silicon nitride film, and wherein the step of treating the silicon nitride film with an oxygen source converts the carbon-doped silicon nitride into a carbon-doped silicon oxynitride film.
- 8) A film formed according to the method of claim 1 having a dielectric constant (k)
25 of about 6 or less, and a carbon content of about 5 atomic weight % or less as measured by X-ray photoelectron spectroscopy.
- 9) A film of claim 8 having a carbon content of about 5 atomic weight percent or less as measured by X-ray photoelectron spectroscopy.
- 10) A film of claim 9 having a carbon content of about 3 atomic weight percent or
30 less as measured by X-ray photoelectron spectroscopy.

- 11) A film of claim 10 having a carbon content of about 2 atomic weight percent or less as measured by X-ray photoelectron spectroscopy.
- 12) A film of claim 11 having a carbon content of about 1 atomic weight percent or less as measured by X-ray photoelectron spectroscopy.
- 5 13) The method of claim 1 further comprising performing a thermal anneal on the silicon nitride or carbon-doped silicon nitride film at temperatures from about 300 to about 1000°C.
- 14) The method of claim 1 further comprising performing a plasma treatment on the silicon nitride film with an inert gas plasma or hydrogen/inert plasma or nitrogen plasma
10 at a temperature ranging between about 25°C and about 600°C.
- 15) The method of claim 2 further comprising performing a plasma treatment on the carbon-doped silicon nitride film with an inert gas plasma or hydrogen/inert plasma or nitrogen plasma at a temperature ranging between about 25°C and about 600°C.
- 16) The method of claim 6 further comprising performing a plasma treatment on the
15 silicon oxynitride film with an inert gas plasma or hydrogen/inert plasma or nitrogen plasma at a temperature ranging between about 25°C and about 600°C.
- 17) The method of claim 7 further comprising performing a plasma treatment on the carbon-doped silicon oxynitride film with an inert gas plasma or hydrogen/inert plasma or nitrogen plasma at a temperature ranging between about 25°C and about 600°C.
- 20 18) A method for forming a silicon nitride or carbon-doped silicon nitride via a plasma enhanced ALD process, the method comprising:
- a) providing a substrate comprising a surface feature in a reactor;
 - b) introducing into the reactor at least one silicon precursor having one or two Si-C-Si linkages and selected from the
25 group consisting of 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-1,3-disilapropane, 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-
- 30

5 disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, and 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane whereby the silicon precursor reacts on at least a portion of the surface feature of the substrate to provide a chemisorbed layer;

- 10 c) purging the reactor of any unreacted silicon precursors and/or any reaction by-products, using inert gas;
- d) providing a first plasma source into the reactor to react with the chemisorbed layer to form a silicon nitride film that is optionally carbon-doped;
- 15 e) purging the reactor of any further reaction by-products using inert gas;
- f) providing a second plasma source into the reactor to further react and form the silicon nitride film that is optionally carbon-doped;
- 20 g) purging the reactor of any further reaction by-products using inert gas;

wherein the steps b through g are repeated until the silicon nitride film that is optionally carbon-doped reaches a desired thickness, and wherein the reactor is maintained at one or more temperatures ranging from about 25°C to about 600°C.

25 19) The method according to claim 18, wherein the plasma is a plasma comprising an ammonia source and the second plasma is a plasma comprising a nitrogen source.

20) The method according to claim 18, wherein the first plasma is a plasma comprising a nitrogen source and the second plasma is a plasma comprising an ammonia source.

30 21) A stainless steel container housing a composition comprising at least one silicon precursor having one or two Si-C-Si linkages and selected from the group consisting of 1,1,1,3,3,3-hexachloro-2-methyl-1,3-disilapropane, 1,1,1,3,3,3-hexachloro-2,2-dimethyl-

1,3-disilapropane, 1,1,1,3,3-pentachloro-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilabutane, 1,1,1,3,3-pentachloro-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-methyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2,2-dimethyl-1,3-disilapentane, 1,1,1,3,3-pentachloro-2-ethyl-1,3-disilapentane, 1,1,1,3,3,5,5-heptachloro-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-3,3-dimethyl-1,3,5-trisilahexane, 1,1,1,5,5-pentachloro-1,3,5-trisilahexane, and 2,2,4,6,6-pentachloro-4-methyl-2,4,6-trisilaheptane.

22) The stainless steel container of claim 21 further housing an inert head-space gas selected from the group consisting of helium, argon, nitrogen and combinations thereof.

10

23) A silicon nitride or carbon-doped silicon nitride film suitable for semiconductor industry or display applications and deposited using the method of claim 1.

24) A silicon nitride or carbon-doped silicon nitride film suitable for semiconductor industry or display applications and deposited using the method of claim 18.

15

A. CLASSIFICATION OF SUBJECT MATTER**C23C 16/455(2006.01)i, C23C 16/34(2006.01)i, C23C 16/56(2006.01)i, H01L 21/02(2006.01)i, C07F 7/12(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C23C 16/455; C23C 16/34; C23C 16/44; C23C 16/448; C23C 16/513; C23C 16/56; H01L 21/02; H01L 21/318; C07F 7/12

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & keywords: low carbon, silicon nitride, film, silicon precursor, ALD

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KR 10-2018-0034581 A (VERSUM MATERIALS US, L.L.C.) 04 April 2018 paragraph [0003], [0063]-[0064], [0130]-[0131] and claims 1, 3, 5, 24-25	23-24
Y		1-7, 13-20, 22
X	US 2018-0033614 A1 (VERSUM MATERIALS US, L.L.C.) 01 February 2018 paragraphs [0048], [0056]-[0059] and claims 1, 17-18	21, 23-24
Y		1-7, 13-20, 22
X	US 2011-0256734 A1 (HAUSMANN et al.) 20 October 2011 paragraphs [0005]-[0008], [0031], [0072], [0120], [0115], [0125]	8-12, 23-24
X	WO 2016-149541 A1 (APPLIED MATERIALS, INC.) 22 September 2016 claims 1, 5	23-24
Y		18-20
X	US 2013-0078376 A1 (HIGASHINO et al.) 28 March 2013 paragraph [0003] and claim 1	23-24

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"D" document cited by the applicant in the international application

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

17 January 2020 (17.01.2020)

Date of mailing of the international search report

17 January 2020 (17.01.2020)

Name and mailing address of the ISA/KR

International Application Division

Korean Intellectual Property Office

189 Cheongsa-ro, Seo-gu, Daejeon, 35208, Republic of Korea



Facsimile No. +82-42-481-8578

Authorized officer

LEE, Eon Su

Telephone No. +82-42-481-8539



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2019/054268

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
KR 10-2018-0034581 A	04/04/2018	CN 107923040 A	17/04/2018
		EP 3329032 A1	06/06/2018
		JP 2018-523753 A	23/08/2018
		JP 6600074 B2	30/10/2019
		TW 201712141 A	01/04/2017
		TW 201809338 A	16/03/2018
		TW I626329 B	11/06/2018
		US 2019-0085451 A1	21/03/2019
		WO 2017-023693 A1	09/02/2017
		US 2018-0033614 A1	01/02/2018
EP 3491167 A1	05/06/2019		
JP 2019-527483 A	26/09/2019		
KR 10-2019-0025060 A	08/03/2019		
SG 11201900319 A	27/02/2019		
TW 201804012 A	01/02/2018		
TW 201900916 A	01/01/2019		
TW I637075 B	01/10/2018		
WO 2018-022719 A1	01/02/2018		
US 2011-0256734 A1	20/10/2011		
		CN 103890910 A	25/06/2014
		CN 104517892 A	15/04/2015
		CN 107342216 A	10/11/2017
		CN 107665811 A	06/02/2018
		JP 2014-112668 A	19/06/2014
		JP 2015-111668 A	18/06/2015
		JP 2018-011067 A	18/01/2018
		KR 10-2013-0055606 A	28/05/2013
		KR 10-2014-0059751 A	16/05/2014
		KR 10-2015-0037662 A	08/04/2015
		KR 10-2017-0089040 A	02/08/2017
		KR 10-2019-0049906 A	09/05/2019
		SG 10201408801 A	30/07/2015
		SG 10201607194 A	28/10/2016
		SG 10201807090 A	27/09/2018
		SG 11201400633 A	28/08/2014
		SG 184566 A1	29/11/2012
		SG 195501 A1	30/12/2013
		SG 2013083241 A	27/06/2014
		TW 201144475 A	16/12/2011
		TW 201207148 A	16/02/2012
		TW 201327679 A	01/07/2013
		TW 201411845 A	16/03/2014
		TW 201526104 A	01/07/2015
		TW 201603120 A	16/01/2016
		TW 201735162 A	01/10/2017
		TW 201809345 A	16/03/2018
		US 2011-0256724 A1	20/10/2011

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2019/054268

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		US 2012-0009802 A1	12/01/2012
		US 2013-0040447 A1	14/02/2013
		US 2014-0051262 A9	20/02/2014
		US 2015-0126042 A1	07/05/2015
		US 2016-0118246 A1	28/04/2016
		US 2017-0148628 A1	25/05/2017
		US 2018-0158683 A1	07/06/2018
		WO 2011-130174 A1	20/10/2011
		WO 2013-032786 A2	07/03/2013
WO 2016-149541 A1	22/09/2016	CN 107430992 A	01/12/2017
		JP 2018-511700 A	26/04/2018
		KR 10-2017-0126494 A	17/11/2017
		TW 201636453 A	16/10/2016
		US 10096466 B2	09/10/2018
		US 2016-0276150 A1	22/09/2016
US 2013-0078376 A1	28/03/2013	CN 102471885 A	23/05/2012
		EP 2553141 A2	06/02/2013
		EP 2730676 A1	14/05/2014
		JP 2013-524522 A	17/06/2013
		JP 5815669 B2	17/11/2015
		KR 10-1226876 B1	28/01/2013
		KR 10-2012-0028999 A	23/03/2012
		TW 201213597 A	01/04/2012
		TW I498447 B	01/09/2015
		WO 2011-123792 A2	06/10/2011